Improving the Hydrolytic Stability of Aryl Cyanate Esters by Examining the Effects of Extreme Environments on Polycyanurate Copolymers

Alasdair O. Crawford, Gabriel Cavalli, Brendan J. Howlin, and Ian Hamerton*

Fig. S1. Images of selected blends between *1-3*.



Fig. S2. ***[1_x-2_y]*** **H_2O absorbed (%) *vs.* time (√hrs) at 75 % RH**



Fig. S3. *[3_x-1_y]* **H_2O absorbed (%)** ***vs.*** **time (√hrs) at 75 % RH**



Fig. S4. *[3_x-2_y]* **H_2O absorbed (%)** ***vs.*** **time (√hrs) at 75 % RH**



Fig. S5. Spectral analysis of *[3_x-1_y]*



Fig. S6. Spectral analysis of *[3_x-2_y]*



Fig. S7. ***[1$_x$-2$_y$]*** **H_2O absorbed (%)** ***vs.*** **time (√hrs)**



Fig. S8. ***[3$_x$-1$_y$]*** **H_2O absorbed (%)** ***vs.*** **time (√hrs)**



Fig. S9. ***[3$_x$-2$_y$]*** **H_2O absorbed (%)** ***vs.*** **time (√hrs)**



Fig. S10. DMTA data for unexposed (black), RH (red) and immersion (blue) for the blend [*1*$_{50}$-*2*$_{50}$] showing storage modulus as a function of temperature.



Fig. S11 DMTA data for *1_{70}-2_{30}* (top) and [*1_{70}-2_{30}*] (bottom) showing storage and loss moduli as a function of temperature.



Fig. S12 High resolution images of outgassing in [$(1)_{50}$-$(2)_{50}$]



Fig. S13 Top view (above) and side view (below) of [$(3)_{90}$-$(2)_{10}$] following exposure and DMTA.



Fig. S14 Basic (left) and Acidic (right) environments with immersed [$(3)_{80}$-$(2)_{20}$] (top), surface etching of [$(3)_{80}$-$(2)_{20}$] (bottom) following exposure to NaOH for 3192 hours.

Table S1. Mass uptakes observed in 75.3 % RH studies

Material	Initial mass (M_0)/g	Final mass (M_i)/g	H_2O absorption/%
1$_{50}$-***2***$_{50}$	2.3344	2.3545	0.85
1$_{60}$-***2***$_{40}$	1.9844	1.9996	0.76
1$_{70}$-***2***$_{30}$	1.9211	1.9370	0.82
1$_{80}$-***2***$_{20}$	1.1480	1.1572	0.80
1$_{90}$-***2***$_{10}$	1.3742	1.3843	0.73
3$_{50}$-***1***$_{50}$	2.1897	2.2040	0.65
3$_{60}$-***1***$_{40}$	1.5209	1.5320	0.72
3$_{70}$-***1***$_{30}$	1.9007	1.9163	0.81
3$_{80}$-***1***$_{20}$	2.1262	2.1485	1.04
3$_{90}$-***1***$_{10}$	1.7388	1.7583	1.11
3$_{50}$-***2***$_{50}$	1.4718	1.4858	0.94
3$_{60}$ -***2***$_{40}$	1.9115	1.9301	0.96
3$_{70}$-***2***$_{30}$	1.6132	1.6304	1.06
3$_{80}$-***2***$_{20}$	1.7078	1.7273	1.13
3$_{90}$-***2***$_{10}$	1.9839	2.0132	1.46

Table S2. Mass uptake observed in direct immersion studies

Material	Initial mass (M_0) /g	Final mass (M_i) /g	H_2O absorption/ %
***1**$_{50}$-**2**$_{50}$*	8.9461	9.0833	1.51
***1**$_{60}$-**2**$_{40}$*	13.5747	13.8366	1.89
***1**$_{70}$-**2**$_{30}$*	10.6314	10.827	1.81
***1**$_{80}$-**2**$_{20}$*	12.9197	13.1641	1.86
***1**$_{90}$-**2**$_{10}$*	7.5177	7.6385	1.58
***3**$_{50}$-**1**$_{50}$*	17.2649	17.7285	2.61
***3**$_{60}$-**1**$_{40}$*	17.3742	17.8680	2.76
***3**$_{70}$-**1**$_{30}$*	12.7562	13.1457	2.96
***3**$_{80}$-**1**$_{20}$*	15.4618	15.9268	2.92
***3**$_{90}$-**1**$_{10}$*	13.8261	14.2588	3.03
***3**$_{50}$-**2**$_{50}$*	13.5108	13.8650	2.55
***3**$_{60}$ -**2**$_{40}$*	17.2138	17.6260	2.34
***3**$_{70}$-**2**$_{30}$*	15.4747	15.9267	2.84
***3**$_{80}$-**2**$_{20}$*	11.8710	12.2167	2.83
***3**$_{90}$-**2**$_{10}$*	15.6982	16.1960	3.07

Table S3. Thermogravimetric data for cured binary cyanate ester blends as determined by TGA (nitrogen, 10 K/minute)

Sample	Mass Loss at Temperature (°C)							Y_C (%)
	5 %	10 %	20 %	30 %	40 %	50 %	60 %	
1	413	423	428	435	458	538	575	1.83
2	417	422	430	452	530	571	588	1.89
3	423	434	522	595	620	635	650	1.76
$\mathbf{1}_{50}$-$\mathbf{2}_{50}$	414	422	427	436	484	549	576	2.03
$\mathbf{1}_{60}$-$\mathbf{2}_{40}$	411	419	421	422	429	470	551	1.54
$\mathbf{1}_{70}$-$\mathbf{2}_{30}$	416	425	427	436	470	542	570	1.45
$\mathbf{1}_{80}$-$\mathbf{2}_{20}$	413	425	430	438	489	552	579	1.22
$\mathbf{1}_{90}$-$\mathbf{2}_{10}$	410	424	428	435	458	530	552	1.76
$\mathbf{1}_{30}$-$\mathbf{2}_{50}$	416	425	441	522	572	595	608	138
$\mathbf{1}_{60}$-$\mathbf{2}_{40}$	419	426	460	552	592	610	622	1.59
$\mathbf{3}_{70}$-$\mathbf{1}_{30}$	420	429	498	573	604	621	635	1.65
$\mathbf{3}_{80}$-$\mathbf{1}_{20}$	420	431	498	578	609	625	640	1.33
$\mathbf{3}_{90}$-$\mathbf{1}_{10}$	419	434	515	585	603	619	633	1.67
$\mathbf{3}_{50}$-$\mathbf{2}_{50}$	420	430	484	558	592	608	621	1.41
$\mathbf{3}_{60}$-$\mathbf{2}_{40}$	420	432	489	560	594	612	624	1.75
$\mathbf{3}_{70}$-$\mathbf{2}_{30}$	408	423	429	487	555	587	604	1.47
$\mathbf{3}_{80}$-$\mathbf{2}_{20}$	420	434	513	574	603	619	633	1.58
$\mathbf{3}_{90}$-$\mathbf{2}_{10}$	418	433	508	566	597	614	628	1.34

Y_C = Char yield measured at 800 °C

Table S4. Mass uptakes observed in acid/base studies

Material	Initial mass (M_0) /g		Final mass (M_i) /g		Mass change /%	
	H_2SO_4	NaOH	H_2SO_4	NaOH	H_2SO_4	NaOH
***1**$_{50}$-**2**$_{50}$*	2.086	2.208	2.1097	2.2348	+1.01	+1.01
***1**$_{60}$-**2**$_{40}$*	1.672	1.449	1.6915	1.4670	+1.01	+1.01
***1**$_{70}$-**2**$_{30}$*	2.289	2.363	2.1350	2.3897	+1.01	+1.01
***1**$_{80}$-**2**$_{20}$*	1.892	1.768	1.9118	1.7904	+1.01	+1.02
***1**$_{90}$-**2**$_{10}$*	0.641	0.481	0.6460	0.4865	+1.01	+1.01
***3**$_{50}$-**1**$_{50}$*	1.776	1.750	1.7950	1.7700	+1.01	+1.01
***3**$_{60}$-**1**$_{40}$*	1.816	2.370	1.8365	2.4016	+1.01	+1.01
***3**$_{70}$-**1**$_{30}$*	2.217	1.458	2.2395	1.4773	+1.01	+1.01
***3**$_{80}$-**1**$_{20}$*	1.909	2.427	1.9307	2.4620	+1.01	+1.01
***3**$_{90}$-**1**$_{10}$*	1.720	1.889	1.7388	1.9242	+1.01	+1.02
***3**$_{50}$-**2**$_{50}$*	1.254	1.327	1.2648	1.3380	+1.01	+1.01
***3**$_{60}$ -**2**$_{40}$*	1.335	0.970	1.3462	0.9810	+1.01	+1.01
***3**$_{70}$-**2**$_{30}$*	1.930	2.052	1.946	2.0761	+1.01	+1.01
***3**$_{80}$-**2**$_{20}$*	1.703	1.671	1.7265	1.6909	+1.01	+1.01
***3**$_{90}$-**2**$_{10}$*	1.523	1.398	1.5408	1.4282	+1.01	+1.02